

**FOR CONTRACT NO.: 03-4M1604
PROJECT ID: 0300020056**

INFORMATION HANDOUT

MATERIALS INFORMATION

**MATERIALS HANDOUT INFORMATION
(SITE INVESTIGATION)**

ROUTE: 03-But-32-11.3/R15.5

MATERIALS HANDOUT INFORMATION

**Contract Number
03-4M1604**

**03-BUT-32
PM 11.3/R15.5**

**Cold In-Place Recycling
Hot Mix Asphalt**

TABLE OF CONTENTS

Cover Sheet	1
Summary of Investigations	2

Summary of Investigations

Investigations carried out on the existing road, BUT-32 PM 11.3/R15.5; indicate that these materials are suitable for cold in-place recycling. Coring tests conducted on subject roadbed indicate that the engineering properties of these materials may be improved to provide sufficient strength required to extend the life of this pavement for one to five years by recycling the upper 0.17' with asphalt emulsion and capping with 0.15' of hot mix asphalt.

The general structural section, from the bottom up, is native material, and hot mix asphalt. Cores indicated a depth of hot mix asphalt that ranged from 0.21' to 0.43'. Core samples taken were uniform in appearance.

The existing AC appears to be severely oxidized with transverse and longitudinal cracking. There is alligator and block cracking throughout the project.

Any reliance placed by the contractor on this information shall be at their own risk and they shall undertake their own separate testing program to determine the materials present and conditions prevailing at the time of construction.

